

Oct 2000	KAMI
----------	------

SISTEMUL DE FINISAJE KAMI

KAMI
PLEGEL ROOF®

FINISAJ Terra

TerraPLEGEL
Hi'load

Vopsea-strat final de inchidere	30-35	µm
Nisip cuartos	-	
Finisaj de bază pentru nisip	30-35	µm
Poliester	20-25	µm
Grund/Amorsa	3-7	µm
Zinc	20	µm
Otel	0.5/0.90	mm
Zinc	20	µm
Grund/Amorsa	3-7	µm
Strat epoxidic	7	µm

KAMI Colour Coating, KCC

PlusPLEGEL

Strat final poliesteric	25-30	µm
Poliester	20-25	µm
Grund/Amorsa	3-7	µm
Zinc	20	µm
Otel	0.5/0.90	mm
Zinc	20	µm
Grund/Amorsa	3-7	µm
Strat epoxidic	7	µm

PLASTISOL 175 µm

PLEGEL
TP-20
TP-45

Plastisol	175	µm
Grund/Amorsă	3-7	µm
Zinc	20	µm
Otel	0.5/0.6	mm
Zinc	20	µm
Grund/Amorsă	3-7	µm
Strat epoxidic	7	µm

POLIESTER

PLEGEL
TP-20
TP-45
S-Dek

Poliester	20-25	µm
Grund/Amorsa	3-7	µm
Zinc	20	µm
Otel	0.45/0.5/0.6/0.90mm	
Zinc	20	µm
Grund/Amorsa	3-7	µm
Strat epoxidic	7	µm

Finisaj POLIESTER Mat

PLEGEL
S-Dek

Strat final Poliester Mat	30-35	µm
Grund/Amorsa	3-7	µm
Zinc	20	µm
Otel	0.5	mm
Zinc	20	µm
Grund/Amorsa	3-7	µm
Strat epoxidic	7	µm

Poliester metalizat

S-Dek Aluminiu
AluPLEGEL
TP-20 Aluminiu
TP-45 Aluminiu

Poliester metalizat	20 - 25	µm
Grund	5	µm
Aluminiu	0.5/0.6	mm
Grund	5	µm

Finisajele produselor sunt aceleasi indiferent de grosimea tablei.

KAMI PLEGEL ROOF, P.O.Box 518, SE-169 29 SOLNA, Suedia

Telefon. +46 8 555 660 77 Fax +46 8 555 661 99

Website: www.plegel.ro Email: vanzari@plegel.ro